



TEST REPORT

Client: Westbury Textiles Australia
 19 Abrams Street
 Balcatta WA 6021 (Perth)
 Australia

Entry No: 112903-01

Date received: 30/08/2019

Client's Description: Fabric: Lazzaro FR LINEN

Test Required: Flammability in accordance with IMO 2010 FTP CODE ANNEX1 PART 8

Pre-treatment: None

Conditioning: A minimum of 88 hours at 50+/-20% Relative Humidity, 20+/-5°C

Date Tests Completed: 13/09/2019

The following test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	Pass
Propane flame	Flaming ceased within the specified two minute period after removal of the propane flame and no progressive smouldering occurred.	Pass

Note: A CMHR 35kg/m³ foam was used as the filling.

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Daniel Young
 Senior Technologist
 13 September 2019

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ Uncertainty budgets for test methods contained within this report are available on request.
- ❖ The results have been obtained for the above test are due to the allowances that have been made based on the uncertainty of the measurement for this test and its associated measurements.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104



Client: Westbury Textiles Australia

Entry No: 112903-01

ANNEX

name and address of the manufacturer/supplier, if known	Westbury Textiles Australia 19 Abrams Street Balcatta WA 6021 (Perth) Australia
type of the furniture, e.g., seat, sofa, office chair, etc	Unknown
name and/or identification of the product tested	Fabric: Lazzaro FR LINEN
description of the sampling procedure, where relevant	Unknown
fabric material: materials such as wool, nylon, polyester, etc., and its composite ratio	Unknown
composition of weave: such as plain, weave, twilled	Unknown
density (number/inch): the number of threads per inch in both warp and weft	Unknown
yarn number count	Unknown
thickness of the fabric in mm	Unknown
mass: weight per unit area (g/m ²)	Unknown
colour and tone: if the product has a pattern, the representative colour shall be described	Unknown
fabric fire retardant treatment	Unknown
filling material (name of the manufacturer, type designation)	TKT cosyfoam
density: weight per unit volume (kg/m ³) and for products where thickness is difficult to measure exactly square density (g/m ²)	35cmhr
filling fire retardant treatment, if any	cmhr
dimensions and mass of cigarette used	0.86g and 0.89g 68mm x 8mm
smouldering rate of the cigarette used	9minutes 42seconds per 50mm
extent of damage (burning and/or char) of specimen measured from the ignition source	Match: 136 x 22 mm and 150 x 40 mm Cigarette: 22 x13 mm and 28x14 mm
occurrence of progressive smouldering	No progressive smouldering occurred

-----End of Document-----