

Confidential Report

Our Ref: 23/61257A/07/23







Client:

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 2 August 2023

Our Ref: 23/61257A/07/23 Your Ref: 190723

Page: 1 of 4

Westbury Textiles Australia

19 Abrams Street Balcatta WA 6021 Perth

Australia

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: ---

Date of Receipt: 25 July 2023

Date Test Started: 2 August 2023

Description of Sample: One sample of fabric, which was referenced by the client as;

Antilles - Sand

Stated to be: 100% Polyolefin

Work Requested: We were asked to make the following fire test:

Schedule 4, Part 1, "The Cigarette Test" of The Furniture and Furnishings (Fire) (Safety) Regulations 1988.

- subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the items tested.





1066



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 2 August 2023

Our Ref: 23/61257A/07/23 Your Ref: 190723

200720

Page: 2 of 4

Client: Westbury Textiles Australia

Testing to Schedule 4, Part 1, "The Cigarette Test" of The Furniture and Furnishings (Fire) (Safety) Regulations 1988 No. 132 SI No. 1324 (as amended by SI 1989 No. 2358, SI 1993 No. 207 & SI 2010 No. 2205), using BS 5852: Part 1: 1979

Pre-Treatment

The material received no pre-treatment as the fabric is stated to not have an FR treatment.

Conditioning

All materials used were conditioned in the environment specified in Clause 7 of BS 5852: Part 1: 1979 "Methods of test for the ignitability by smokers materials of upholstered composites for seating."

Testing

The material was tested according to BS 5852: Part 1: 1979 "Methods of test for the ignitability by smokers materials of upholstered composites for seating."

The results of BS 5852: Part 1: 1979 relate only to the ignitability of the combination of materials under the particular conditions of test, they are not intended as a means of assessing the full potential fire hazard of the materials in use.







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 2 August 2023

Our Ref: 23/61257A/07/23 Your Ref: 190723

Page: 3 of 4

Client: Westbury Textiles Australia

Results of Cigarette Test - Source 0

The sample was tested over combustion modified polyurethane foam with a density of approximately 22-24kg/m³.

Specimen No.	1	2
Time of Ignition (min)		
Extinction Time (Smouldering) (min)	22	22
Time to cover split (min)	DNO	DNO
Melting	Yes	Yes
Dripping	No	No
Charring	Yes	Yes
Progressive smouldering on final inspection	No	No

Requirements - No flaming or progressive smouldering within a period of 1 hour from placement of the cigarette.

Result of the Cigarette Test: Pass

Acronyms

DNP – Did not propagate EC – Escalating combustion ME – Manually extinguished ES – Escalating smouldering DNS – Material did not split BTE – Burnt to extremities DNO – Did not observe time of event

Comment

The sample meets the flammability requirements of Schedule 4, Part 1, "The Cigarette Test" of the Furniture and Furnishings (Fire) (Safety) Regulation 1988 (as amended) S.I. No. 1324.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.





1066



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 2 August 2023

Our Ref: 23/61257A/07/23 Your Ref: 190723

Page: 4 of 4

Client: Westbury Textiles Australia

Uncertainty Budget

Timings: ±2 seconds. Measurements: ±2mm.

Reported by:...... R Greasley, Laboratory Technician

Countersigned by: P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.





1066