



Confidential Report

Our Ref: 23/61135F/06/23





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 June 2023

Our Ref: 23/61135F/06/23
Your Ref: #120623

Page: 1 of 5

Client: **Westbury Textiles**

19 Abrams Street
Balcatta
WA
6021
Perth
Australia

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: #120623

Date of Receipt: 19 June 2023

Date Test Started: 30 June 2023

Description of Sample: One sample of fabric, which was referenced by the client as;

Malibu - Raffia

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the items tested.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 30 June 2023
 Our Ref: 23/61135F/06/23
 Your Ref: #120623
 Page: 2 of 5

Client: **Westbury Textiles**

Product Description

Company Name	Westbury Textiles
FABRIC	
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Sofa upholstery fabric
Name and/or Identification of the Product Tested	Malibu
Materials of the Product and its Composite Ratio (i)	100% Polyolefin
Composition of Weave (ii)	Plain Weave
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Warp: 44, Weft: 36 threads per inch
Yarn Number Count	N/S
Thickness (mm)	2mm
Mass per Unit Area (g/m ²)	480 gms
Colour and Tone (iii)	Raffia
Method and Quantity of Fire Retardant Treatment	No Treatment
FILLINGS	
Material (Name of Manufacturer, Type Designation)	N/S
Type of Filling Material (eg. Foam, Polyester Fibre etc.)	N/S
Weight per Unit Volume (kg/m ³)	N/S
Method and Quantity of Fire Retardant Treatment	N/S

- (i) Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 June 2023

Our Ref: 23/61135F/06/23
Your Ref: #120623

Page: 3 of 5

Client: **Westbury Textiles**

Testing to IMO FTP Code 2010 : Part 8 Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $23\pm 2^{\circ}\text{C}$ temperature and $50\pm 5\%$ relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m^3 and 21°C .

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately $34\text{-}36\text{kg}/\text{m}^3$.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm)	69mm x 8.0mm
Mass (g)	0.95g
Smouldering Rate (mins/secs)	10m 05s



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 30 June 2023

Our Ref: 23/61135F/06/23
 Your Ref: #120623

Page: 4 of 5

Client: **Westbury Textiles**

Results

Cigarette Test – Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	21	22
Time of cover split	DNO	DNO
Melting (Yes/No)	Yes	Yes
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNO	DNO
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	4	4
Extinction time of flames after removal of burner (s)	2	2
Time to Cover Split (s)	7	7
Melting (Yes/No)	Yes	Yes
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:	--	--
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate
 ES – Escalating smouldering
 BTE – Burnt to extremities

EC – Escalating combustion
 DNS – Material did not split

ME – Manually extinguished
 DNO – Did not observe time of event



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
 A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
 The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
 Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 June 2023

Our Ref: 23/61135F/06/23
Your Ref: #120623

Page: 5 of 5

Client: **Westbury Textiles**

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Uncertainty Budget

Measurements: $\pm 2\text{mm}$
Timings: ± 2 seconds.

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.