



TEST REPORT

Client: Westbury Textiles Australia
19 Abrams Street
Balcatta WA 6021 (Perth)
Australia

Entry No: 112954

Date received: 30/08/2019

Client's Description: Fabric: Massimo Ivory

Test Required: Flammability

Pre-treatment: None

Conditioning: A minimum of 24 hours at 50+/-5% Relative Humidity, 23+/-2°C

Date Tests Completed: 19/09/2019

Method of Test: BS EN 1021-1:2014 – smouldering cigarette
BS EN 1021-2:2014 – match flame equivalent

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	Pass
Match flame equivalent	Forcibly extinguished after 120	Fail

Note: 35 kg/m3 CMHR Foam was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Daniel Young
Senior Technologist
20 September 2019

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
- ❖ Uncertainty budgets for test methods contained within this report are available on request.
- ❖ The results have been obtained for the above test are due to the allowances that have been made based on the uncertainty of the measurement for this test and its associated measurements.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104