



Date of Issue: 1/11/2021 Report Number: 20-003689

Revision Number:1

Date Order Received: 11/12/2020

For the Account of: Westbury Textiles USA Inc

c/o Sobel & Co

50 Tice Blvd STE 175

Woodcliff Lake, NJ 07677-7681

Client's Identification:	ERBA TREVIRA

## **CERTIFICATE OF TESTING**

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2019 – Test #1

## **TEST RESULTS**

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	7.9	5.2	34	0.0	0.0
2	7.8	5.6	28	0.0	0.0
3	7.8	5.1	35	0.0	0.0
4	7.9	5.5	30	0.0	0.0
5	7.9	4.8	39	0.0	0.0
6	7.9	4.9	38	0.0	0.0
7	7.9	5.1	35	0.0	0.0
8	7.8	5.2	33	0.0	0.0
9	7.8	5.3	32	0.0	0.0
10	7.9	5.8	27	0.0	0.0
Average	7.9	5.3	33	0.0	0.0

approximate weight (oz./sq. yd): 3.9		Standard Deviation: 4.0	<b>Average + 3 SD:</b> 45.0	
Product Configuration: ☑ Single Layer Conditioning: ☑ Oven at 220°F Intended End-use (if known & other than drapery): D		☐ Multi Layer for minimum 30 minutes rapery	☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours	
Where fragme seconds per seconds per seconds per seconds individual specific with the specific per recorded as second secon	be recorded; however, it is not ents or residues of specimens specimen for the sample of 10 erage weight loss of the 10 specimens will be listed as a failured ecimens do not demonstrate p s passing this test and shall be	specimens, the material shall be r ecimens in a sample is greater tha re if it exceeds mean + 3 SD	mber continue to burn for more than an average of 2 ecorded as failing. (Flaming Drip) an 40 percent, the material shall be recorded as failing. ther of the conditions indicated above, the material shall	
	Complies Does Not Comply			
pecified by the standar		btained after testing specimen in	accordance with the procedures and equipment	
Berta Stiver				
uthorized Signature			Date Order Completed: 11/16/2020	

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1