



Report Number: 19-002811

Revision Number:1

Date Order Received: 05/23/2019

For the Account of: Westbury Textiles USA Inc

c/o Sobel & Co 50 Tice Blvd STE 175

Woodcliff Lake, NJ 07677-7681

Client's Identification:	Malibu Outdoor
--------------------------	----------------

## **CERTIFICATE OF TESTING**

**TEST PERFORMED:** California Technical Bulletin 117: June 2013 – Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture – Cover Fabric Test

## **TEST RESULTS**

	Specimen	Char Length (in)	Extinguished in 45 Minutes
Initial Test	1	1	Υ
	2	0.9	Υ
	3	1	Υ

**NOTES** 

**Test Conditions:** 70 ±5°F, 50 ±5% Relative Humidity

Dev-009: Used SRM 1196 Equivalent YES

Lot # 18390120015

## ACCEPTANCE CRITERIA

A material is considered to pass or fail based on the following criteria:

- 1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
  - a. The mock-up test specimen continues to smolder after the 45 minute test duration
  - b. A vertical char length of more than 1.8 inches (45mm) develops on the cover fabric
  - c. The mock-up test specimen transitions to open flaming
- 2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn their full length and are no longer smoldering
- 3. If more than one initial specimen fails, the cover fabric fails the test
- If any one of the three initial specimens fails, repeat the test on additional three specimens
- 5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test

CONCLUSION	Based on the above Results and Acceptance Criteria, the item tested is
	☑ Pass
	☐ Fail

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Date Order Completed: 06/03/2019