



TEST REPORT

Client: Westbury Textiles Australia
19 Abrams Street
Balcatta WA 6021 (Perth)
Australia

Entry No: 113039

Date received: 30/08/2019

Client's Description: Fabric: Biella Trevira Crema

Test Required: Flammability BS 5867-2: Type C: 2008

Pre-treatment: None

Conditioning: A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C

Date Tests Completed: 26/09/2019

Method of Test: BS EN ISO 15025: 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

5 Second Application				
Both Face and back tested	Fabric Length direction		Fabric Width direction	
Specimen number	Face	Back	Face	Back
Flame reached an edge (✓ or X)	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X
Duration of flaming (s)	0	0	0	0
Duration of afterglow (s)	0	0	0	0

15 Second Application				
Both Face and back tested	Fabric Length direction		Fabric Width direction	
Specimen number	Face	Back	Face	Back
Flame reached an edge (✓ or X)	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X
Duration of flaming (s)	0	0	0	0
Duration of afterglow (s)	0	0	0	0

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Daniel Young
Senior Technologist
26 September 2019

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ Uncertainty budgets for test methods contained within this report are available on request.
- ❖ The results have been obtained for the above test are due to the allowances that have been made based on the uncertainty of the measurement for this test and its associated measurements.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104



Client: Westbury Textiles Australia

Entry No: 113039

20 Second Application				
Both Face and back tested	Fabric Length direction		Fabric Width direction	
Specimen number	Face	Back	Face	Back
Flame reached an edge (✓ or X)	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X
Duration of flaming (s)	0	0	0	0
Duration of afterglow (s)	0	0	0	0

30 Second Application				
Both Face and back tested	Fabric Length direction		Fabric Width direction	
Specimen number	Face	Back	Face	Back
Flame reached an edge (✓ or X)	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X
Duration of flaming (s)	0	0	0	0
Duration of afterglow (s)	0	0	0	0

Flame application times 5, 15, 20 and 30 seconds using propane gas

Comments

On the basis of the tests carried out this sample of fabric meets the Type C requirements of BS 5867-2: 2008

-----End of Document-----